

DEUREX® A 26 P

TECHNICAL INFORMATION

Chemical description: Vegetable Erucamide wax

Application: Plastics industry (e.g. PVC, PE and PP)

Paper Industry

- Defoamer for the production of paper

Metal processing

- Surface lubricant for metal production

Printing inks

Improves the dye distribution

- Good overprintability and wet printing properties

Rubber industry

- Reduction of the tacks in CSM roller mixer

- Mold release agents

Increases the abrasion resistance

- Reduction of sulphurization

Properties: - Excellent slip

- Lubricant, release agent

- Very good Anti-blocking properties

- Processing aid

- Abrasion resistance

- Dust free

Technical Data: Colour: Light yellow

Consistencies: **DEUREX A 26 P** = Powder

| | Minimum | Maximum | Method |
|---------------------|------------------------|--------------------------|-------------|
| Drop point*: | 83 °C | 95 °C | ASTM D 3954 |
| Acid value*: | | 1 mg KOH/g | ASTM D 1386 |
| Viscosity (140 °C): | | 12 mPas | ISO 3219 |
| Penetration: | | 45.0 mm*10 ⁻¹ | ASTM D 1321 |
| Density (23 °C): | 0.87 g/cm ³ | 0.88 g/cm ³ | ISO 1183 |

^{*} Part of certificate of analysis

Approvals: Food contact approvals

Alternative products: See https://www.deurex.com/productsearch/DEUREX-A-26-P/

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

③ - registered trademark by DEUREX

Revision: