

## DEUREX® F 6314 M

### TECHNICAL INFORMATION

- Chemical description:** Micronized polyolefin wax, spot coated with micronized PTFE
- Benefits:**
- Wax surface coated with stoichiometrically calculated amount of PTFE
  - Product migrates to the surface of aqueous and solvent-based systems
- Applications:**
- Paints and coatings
- Powder coatings, can coatings, furniture and parquet coatings
  - Automotive and industrial coatings, decorative paints
- Printing inks
- Especially for sheetfed offset inks as well as flexo and gravure inks
- Properties:**
- Very hard wax
  - Very good abrasion and scratch resistance
  - Easy to disperse without heating
  - Avoid high temperatures over 50°C

**Technical data:**

Colour: White  
Delivery form: **DEUREX® F 6314 M** = Micronized powder

	Minimum	Maximum	Method
Particle size*:		98% < 14 µm	LV 5 (ISO 13320)
Typical value:		50 % ~ 6 µm	
Drop point <sub>(wax)</sub> *:	110 °C	120 °C	LV 12 (DGF M-III 3)
Density (23 °C) <sub>(wax)</sub> :	0.94 g/cm <sup>3</sup>	0.95 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)
Melting point (PTFE)*:	320 °C	340 °C	LV 5 (ASTM D4591)
Density (23 °C) <sub>(PTFE)</sub> :	2.15 g/cm <sup>3</sup>	2.25 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)

\* Part of certificate of analysis

**Approvals:** DEUREX® F 6314 M is approved for the production of commodities intended to come into contact with food.

EU: Regulation (EU) 10/2011 dated 14th January 2011  
(Approvals with regard to limitations and migration values in the final application)

**Alternative delivery forms:**

**DEUREX® F 6008 M** – Micronized powder (100% PTFE)  
**DEUREX® F 6114 M** – Double coated, wax is completely embedded in PTFE  
**DEUREX® F 6214 M** – Fully coated, wax is completely coated with PTFE  
**DEUREX® F 6414 M** – Eco coated, wax with a standard does of PTFE  
**DEUREX® F 6001 W** – Water-based dispersion of a micronized PTFE

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.  
 © - registered trademark by DEUREX