

## DEUREX<sup>®</sup> T 15

### TECHNICAL INFORMATION

<b>Chemical description:</b>	Fischer-Tropsch Paraffin wax		
<b>Applications:</b>	<u>Rubber</u> - Protection against sun light and ozone  <u>Raw material for Emulsions</u> - Textile industry - Care products, polishes - Leather industry - Paper industry  <u>Fertilizer industry</u> - Coating of fertilizers, - Retarding agent		
<b>Properties:</b>	- Release agent - Processing aid		
<b>Benefits:</b>	- Soft and flexible wax - Nearly oil-free paraffin - Chemical Stability - UV resistance		
<b>Technical data:</b>	Colour:	White	
	Delivery form:	Slabs	
		Minimum	Maximum
	Drop point*:	47 °C	55 °C
			Method
			LV 12 (DGF M-III 3)
	Penetration:		62 mm*10 <sup>-1</sup> LV 4 (DIN 51579)
	Density (23 °C):	0.85 g/cm <sup>3</sup>	0.90 g/cm <sup>3</sup> LV 3 (DIN EN ISO 1183)
	* Part of certificate of analysis		
<b>Approvals:</b>	USA: FDA 21 CFR § 172.886 (Approvals with regard to limitations and migration values in the final application)		
<b>Alternative delivery form:</b>	DEUREX <sup>®</sup> T 1601 W – Paraffin wax emulsion, 98% < 1µm		

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.  
 © - registered trademark by DEUREX