

DEUREX® F 64 TEX

TECHNICAL INFORMATION

- Chemical description:** Structurant PTFE, embedded in polymers (Eco coated)
- Benefits:**
- PTFE coated polyolefin wax
 - Wax features dominate
 - Uniform texture at low dosages
 - Admixture 0.2% – 1.5%, depending on desired final properties
 - Easy to disperse in powder coatings
- Applications:** Powder coatings
- Texturing agent for hybrid systems (Polyester, Polyurethane)
- Properties:**
- Allows a wide selection of controlled textures
 - High abrasion resistance
 - High scratch resistance
 - Uniform surface feel
 - Increased lubricity by reducing of the friction coefficient
 - Improved temperature and solvent resistance
 - Recoatable without affecting the texture

Technical data:

Colour: White
Delivery form: **DEUREX® F 64 TEX** = Powder

	Minimum	Maximum	Method
Drop point (wax)*:	110 °C	120 °C	LV 12 (DGF M-III 3)
Density (23 °C) (wax):	0.94 g/cm ³	0.95 g/cm ³	LV 3 (DIN EN ISO 1183)
Melting point (PTFE)*:	320 °C	340 °C	LV 5 (ASTM D4591)
Density (23 °C) (PTFE):	2.15 g/cm ³	2.25 g/cm ³	LV 3 (DIN EN ISO 1183)
Shelf life:	24 month (In closed, original containers in compliance with storage conditions)		

* Part of certificate of analysis

Alternative delivery forms:

DEUREX® F 60 Micro-Series – Micronized powder with 100% PTFE
DEUREX® F 62 TEX – Fully coated, wax completely coated with PTFE
DEUREX® F 63 TEX – Spot coated, stoichiometrically calculated amount of PTFE
DEUREX® F 6001 W – Water-based dispersion of a micro-sized PTFE

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
 © - registered trademark by DEUREX