

DEUREX[®] EO 47 P

TECHNICAL INFORMATION

Chemical description:	Oxidized HDPE wax		
Production process:	Wet Oxidation		
Applications:	<u>Production of water based emulsions and dispersions for</u> <ul style="list-style-type: none"> - Textile industry (improved sewability and cutting of textiles, improves machine lifetime) - Care products, polishes - Coatings and inks (e.g. overprint varnishes) - Leather & paper industry 		
Benefits:	<ul style="list-style-type: none"> - White powder, transparent melt - Finer particle size compared to DEUREX[®] EO 47 K - For the production of very fine and transparent emulsions - Easier to emulsify than DEUREX[®] EO 46 P due to higher acid value 		
Properties:	<ul style="list-style-type: none"> - Improves the surface properties including scratch resistance by lowering the coefficient of friction - High density and high drop point - Excellent abrasion resistance - High blocking resistance and UV stability - Improves processing time and adhesion to substrate - Improves slip 		
Technical data:	Color:	Off-white	
	Delivery form:	DEUREX EO 47 P	= Powder
		Minimum	Maximum
	Drop point:	132 °C	135 °C
	Acid value*:	33 mgKOH/g	37 mgKOH/g
	Penetration:		0.5 mm*10 ⁻¹
	Viscosity (140 °C)*:		1.600 mPas
	Density (23 °C):	0.97 g/cm ³	0.99 g/cm ³
			Method
			ASTM D 3954
			ASTM D 1386
			ASTM D 1321
			ISO 3219
			ISO 1183
	* Part of certificate of analysis		
Approvals:	Food contact approvals		
Alternative products:	See https://www.deurex.com/productsearch/DEUREX-EO-47-P/		

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

© - registered trademark by DEUREX