

DEUREX[®] T 17 G

TECHNICAL INFORMATION

- Chemical description:** Fischer Tropsch wax (Congealing point 70 °C)
- Applications:**
- Hot melts
 - Adjustment of open time
 - Improved Adhesion
 - No stringing
 - PVC
 - Internal and external lubricant
 - Rubber
 - Protection against sun light and ozone
 - Raw material for Emulsions
 - Production of care products, paints and coatings
- Benefits:**
- Crystalline wax with very narrow C-chain distribution
 - Very fast solidification point at 70 °C

Technical data:

Colour: White
Delivery forms: **DEUREX T 17 G** = Granules

	Minimum	Maximum	Method
Drop point*:	75 °C	85 °C	ASTM D 3954
Acid value:		0 mgKOH/g	ASTM D 1386
Viscosity (140 °C):		10 mPas	ISO 3219
Penetration:	10 mm*10 ⁻¹	15 mm*10 ⁻¹	ASTM D 1321
Density (23 °C):	0.85 g/cm ³	0.90 g/cm ³	ISO 1183

* Part of certificate of analysis

Approvals: Food contact approvals

Alternative products: See <https://www.deurex.com/productsearch/DEUREX-T-17-G/>