

## **DEUREX® EO 4530 M**

|   |                  | TECHNICAL INFORMATION  |   |                           |             |  |
|---|------------------|--|---|---------------------------|-------------|--|
| Chemical description:                                 |                  | Micronized oxidized HDPE   |   |                           |             |  |
| Benefits:   |                  | DEUREX <sup>®</sup> EO 45 probably the hardest wax in the world  |   |                           |             |  |
| Applications:<br>Properties:                          |                  | Flexo- and gravure inks<br>Lithographic paste inks<br>Heat set<br>Used in water-based-coatings and inks,<br>UV/EB cured coatings and inks<br>Dry-film lubricants and thinner film applications<br>Powder coatings<br>High temperature stability  |   |                           |             |  |
|   | -<br>-<br>-<br>- | Outstanding abrasion resistance and toughness<br>Very good blocking resistance<br>Friction coefficient might be the best choice from all waxes<br>Excellent antisettling and antifloating properties<br>Highly compatible with aqueous-based systems<br>Non sticky, free flowing matting lubricant |   |                           |             |  |
| Technical data:                                       |                  | Colour:<br>Consistencies:  | White DEUREX <sup>®</sup> EO 4530 M = Micronized powder |                           |             |  |
|   |                  |  | Minimum   | Maximum                   | Method      |  |
| DDC (AVIng)   | 138.0 °C         | Particle size *:<br>Typical value:   |   | 98% < 30 μm<br>50% ~ 9 μm | ISO 13320   |  |
| 15-   |                  | Drop point*:   | 132 °C  | 135 °C                    | ASTM D 3954 |  |
| 10-   |                  | Penetration:   |   | 0.5 mm*10 <sup>-1</sup>   | ASTM D 1321 |  |
| 5   |                  | Density (23 °C):   | 0.97 g/cm <sup>3</sup>                                  | 0.99 g/cm <sup>3</sup>    | ISO 1183    |  |
| 0 [/<br>_20 0 20 40 60 80 100 120 1<br>we produce //C | 140              | * Part of certificate of analys  | is  |                           |             |  |

Approvals:

Alternative products :

Food contact approvals

See https://www.deurex.com/productsearch/DEUREX-EO-4530-M/

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions. (a) - registered trademark by DEUREX