

## **DEUREX® T 18 G**

**TECHNICAL INFORMATION** 

Chemical description: Microcrystalline wax

Applications: PVC

- Lubricant, packaging vegetables, bread, meat, sweets

Cable

Resistance against oilResistance against cold

- Rub resistance

Hot melts

- Adjustment of open time

- Improved adhesion, no stringing

Technical data: Colour: Off-white

Delivery forms: **DEUREX® T 18 G** = Granules

	Minimum	Maximum	Method
Drop point*:	80 °C	85 °C	ASTM D 127
Kin. Viscosity (100 °C):		20 mm²/s	ISO 3104
Penetration*:	10 mm*10 <sup>-1</sup>	25 mm*10 <sup>-1</sup>	DIN 51579
Density (23 °C):	0.75 g/cm³	0.85 g/cm <sup>3</sup>	ISO 12185

<sup>\*</sup> Part of certificate of analysis

**Approvals:** Food contact approvals

Alternative products: See <a href="https://www.deurex.com/productsearch/DEUREX-T-18-G/">https://www.deurex.com/productsearch/DEUREX-T-18-G/</a>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

③ - registered trademark by DEUREX

Revision: