

DEUREX® T 19 K

TECHNICAL INFORMATION

Chemical description:	Fischer Tropsch wax		
Applications:	<u>Hot melts</u> - Adjustment of open time - Improved Adhesion - No stringing <u>PVC</u> - Internal and external lubricant <u>Rubber</u> - Protection against sun light an ozone <u>Raw material for Emulsions</u> - Production of care products, paints and coatings <u>Raw material to produce micronized waxes</u> - Paints and coatings - Increased scratch resistance and slip		
Benefits:	- Crystalline wax with very narrow C-chain distribution - Very fast solidification point at 80 °C		
Technical data:	Colour:	White	
	Delivery forms:	DEUREX® T 19 K	= Fine granules
		Minimum	Maximum
	Drop point*:	92 °C	104 °C
	Acid value:		0 mgKOH/g
	Viscosity (140 °C)*:		15 mPas
	Penetration:		5 mm*10 ⁻¹
	Density (23 °C):	0.89 g/cm ³	0.91 g/cm ³
			Method
			ASTM D 3954
			ASTM D 1386
			ISO 3219
			ASTM D 1321
			ISO 1183
	* Part of certificate of analysis		
Approvals:	Food contact approvals		
Alternative products:	See https://www.deurex.com/productsearch/DEUREX-T-19-K/		

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
 © - registered trademark by DEUREX